

Application No. 10/675,374
Amendment Dated August 6, 2006
Reply to Office Action Dated: June 7, 2006

125640-1

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the Application:

Listing of Claims:

1. (Currently Amended) A green product for use in fabricating a ceramic article, comprising a ceramic powder immobilized within a silicone matrix, wherein the silicone matrix comprises one or more cross linked or polymerized silicone monomers and/or oligomers which comprise a volume of about 50% to about 75%, based on the total volume of green product, wherein the one or more cross linked or polymerized silicone monomers and/or oligomers, prior to cross linking and/or polymerization, contain at least three alkenyl reactive functional groups or at least three hydride reactive functional groups per mole of monomer or oligomer; have a viscosity of about 1 to about 1,000 centistokes, and are substantially free of solvent ~~an alkenyl reactive functional group and a hydride reactive functional group.~~

2. (Original) The green product according to Claim 1, wherein the hydride reactive functional groups and the alkenyl reactive functional groups are present at a molar ratio of 0.5 to 3.

3. (Canceled)

4. (Canceled)

5. (Currently Amended) The green product according to Claim 1, wherein the ceramic powder comprises at least one material selected from the group consisting of alumina, fused alumina, fused silica, magnesia, zirconia, spinels, mullite, glass frits, tungsten carbide, silicon carbide, boron nitride, silicon nitride, and combinations comprising at least one of the foregoing ceramics.

6. (Currently Amended) The green product according to Claim 5, wherein the ceramic powder further comprises comprising at least one material

Application No. 10/675,374
 Amendment Dated August 6, 2006
 Reply to Office Action Dated: June 7, 2006


125640-1

selected from the group consisting of aluminum, yttrium, hafnium, yttrium aluminate, rare earth aluminates, colloidal silica, magnesium, zirconium, and ~~or~~ combinations comprising at least one of the foregoing.

7. (Canceled)

8. (Currently Amended) The green product according to Claim 1, wherein the one or more silicone monomers and/or oligomers having the hydride functional group is selected from the group consisting of:

a polyfunctional hydride siloxane of formula:



wherein R is a monovalent hydrocarbon, R''' is a monovalent hydrocarbon or hydrogen, ~~and a and b~~ $a = 0$ to 20, inclusive, and $b = 1$ to 80, inclusive, wherein a and b are selected to provide a fluid with maximum viscosity of 1,000 centistokes,

an alkyl/hydride cyclosiloxane ~~cyclosiloxanes~~ of formula:



wherein x is an integer 3 to 18 inclusive,


a functional hydride siloxane ~~siloxanes~~ of formula:

Application No. 10/675,374

125640-1


Amendment Dated August 6, 2006

Reply to Office Action Dated: June 7, 2006



wherein a ratio of the sum of $(c+d+e+g)/f$ is ≥ 2 ,


a terminal hydride siloxane of formula:



wherein $n = 0$ to 100, and

mixtures thereof.

9. (Currently Amended) The green product according to Claim 1, wherein the one or more silicone monomers and/or oligomers containing the alkenyl functional group comprises a formula of:




wherein R^1 , R^2 , and R^3 each independently comprise hydrogen or a monovalent hydrocarbon radical, X a divalent hydrocarbon radical, and a is 0 or 1 ~~a whole number having a value between 0 and 8, inclusive.~~

Application No. 10/675,374
 Amendment Dated August 6, 2006
 Reply to Office Action Dated: June 7, 2006

125640-1

10. (Currently Amended) The green product according to Claim 1, wherein the one or more silicone monomers and/or oligomers having the alkenyl functional group is selected from the group consisting of:

polyfunctional siloxanes of formula:




wherein R is a monovalent hydrocarbon, R' is an alkenyl radical, R'' is a monovalent hydrocarbon or an alkenyl radical, $a = 0$ to 20, inclusive, and $b = 1$ to 80, inclusive, wherein a and b are selected to provide a fluid with a maximum viscosity of 1,000 centistokes,

a cyclic alkyl/alkenyl siloxane ~~siloxane~~ of formula:



wherein R and R' are as previously defined; wherein x is an integer 3 to 18 inclusive;

an unsaturated siloxane of formula:



Application No. 10/675,374
Amendment Dated August 6, 2006
Reply to Office Action Dated: June 7, 2006

125640-1

wherein R, R', and R" are as previously defined. ~~Preferably, the ratio of the sum of~~
~~(e+d+e+g)/f is ≥ 2 ;~~

and mixtures thereof.

11. (Canceled)

12. (Original) The green product according to Claim 1, wherein the silicone matrix has a crosslink density as defined by the average molecular mass of the shortest formula repeat unit distance between a reactive hydride or an alkenyl functional crosslink sites of about 30 to about 4,100 grams per mole.

13. (Canceled)

14. (Original) The green product according to Claim 1, wherein the one or more silicone monomers and/or oligomers having the hydride functional group is selected from the group consisting of poly(methylhydrogen)siloxane, poly[(methylhydrogen)-co-(dimethyl)]siloxane; 1,3,5,7-tetramethylcyclotetrasiloxane, 1,3,5,7,9-decamethylcyclopentasiloxane, cyclic methylhydrogen siloxanes; tetrakis(dimethylsiloxy)silane, hydridodimethylsiloxy silicate $[\text{HSi}(\text{CH}_3)_2\text{O}_{1/2}]_2$ (SiO_2), and mixtures thereof.

15. (Original) The green product according to Claim 1, wherein the one or more silicone monomers and/or oligomers having the alkenyl functional group is selected from the group consisting of 1,3-divinyl-tetramethyldisiloxane, hexavinyl-disiloxane, 1,3-divinyltetraphenyldisiloxane, 1,1,3-trivinyltrimethyldisiloxane, 1,3-tetravinyl-dimethyldisiloxane, 1,3,5-trivinyl-1,3,5-trimethylcyclotrisiloxane, 1,3,5,7-tetravinyl-1,3,5,7-tetramethylcyclotetrasiloxane, 1,3-divinyloctaphenylcyclopentasiloxane, and mixtures thereof.

Application No. 10/675,374
 Amendment Dated August 6, 2006
 Reply to Office Action Dated: June 7, 2006

125640-1

16. (Canceled)

17. (Original) An investment casting core fabricated with the green product of Claim 1.

18. (Currently Amended) A process for forming a green product, comprising:

mixing a ceramic powder with silicone monomers and/or oligomers to form a ceramic slurry, wherein the silicone monomers and/or oligomers contain an alkenyl

functionality of formula:
$$\begin{array}{c} \text{R}^1 \\ | \\ -\text{Si}-\text{X}_a-\text{C}=\text{C}- \\ | \quad \quad | \\ \text{R}^2 \quad \quad \text{R}^3 \end{array}$$
, wherein R¹, R², and R³ each independently comprise hydrogen or a monovalent hydrocarbon radical, X a divalent hydrocarbon radical and *a* is 0 or 1 ~~a whole number having a value between 0 and 8, inclusive~~, and a hydride functionality consisting of silicon-hydrogen bonds;

adding a metallic catalyst compound to the ceramic slurry; and

cross linking and/or polymerizing the silicone monomers and/or oligomers to form a rigid silicone matrix.

19. (Original) The process according to Claim 18, wherein mixing the ceramic powder with the silicone monomers and/or oligomers is free of a solvent.

20. (Original) The process according to Claim 18, wherein mixing the ceramic powder with the silicone monomers and/or oligomers first comprises mixing the ceramic powder with a dispersant.


Application No. 10/675,374
 Amendment Dated August 6, 2006
 Reply to Office Action Dated: June 7, 2006

125640-1

21. (Original) The process according to Claim 18, wherein cross linking and/or polymerizing the silicone monomers and/or oligomers to form the rigid silicone matrix comprises heating the ceramic slurry to an elevated temperature.

22. (Currently Amended) The process according to Claim 18, wherein the one or more silicone monomers and/or oligomers containing the alkenyl functional group is selected from the group consisting of:

polyfunctional siloxanes of formula:



wherein R is a monovalent hydrocarbon, R' is an alkenyl radical, R'' is a monovalent hydrocarbon or an alkenyl radical, $a = 0$ to 20, inclusive, and $b = 1$ to 80, inclusive, wherein a and b are selected to provide a fluid with a maximum viscosity of 1,000 centistokes,

a cyclic alkyl/alkenyl siloxane ~~siloxane~~ of formula:




wherein R and R' are as previously defined, and x is an integer 3 to 18 inclusive;

an unsaturated siloxane of formula:

Application No. 10/675,374
 Amendment Dated August 6, 2006
 Reply to Office Action Dated: June 7, 2006

125640-1




wherein R, R', and R'' are as previously defined. Preferably, the ratio of the sum of (c+d+e+g)/f is ≥ 2 ;

and mixtures thereof.

23. (Currently Amended) The process according to Claim 18, wherein the one or more silicone monomers and/or oligomers containing the hydride functional group is selected from the group consisting of:

a polyfunctional hydride siloxane of formula:



wherein R is a monovalent hydrocarbon, R''' is a monovalent hydrocarbon or hydrogen, and a and b a = 0 to 20, inclusive, and b = 1 to 80, inclusive, wherein a and b are selected to provide a fluid with maximum viscosity of 1,000 centistokes,

an alkyl/hydride cyclosiloxanes of formula:




wherein x is an integer 3 to 18 inclusive,

Application No. 10/675,374


125640-1

Amendment Dated August 6, 2006

Reply to Office Action Dated: June 7, 2006

a functional hydride siloxane ~~siloxanes~~ of formula:wherein a ratio of the sum of (c+d+e+g)/f is ≥ 2 ,

a terminal hydride siloxane of formula:



wherein n = 0 to 100, and

mixtures thereof.

24. (Original) The process according to Claim 18, wherein the metallic compound comprises a platinum group metal catalyst.

25. (Original) The process according to Claim 18, further comprising heating the rigid silicone matrix to form a ceramic core having a silica char contained therein.

26. (Original) The process according to Claim 18, wherein the one or more silicone monomers and/or oligomers containing the alkenyl functional group is

Application No. 10/675,374

125640-1

Amendment Dated August 6, 2006

Reply to Office Action Dated: June 7, 2006

selected from the group consisting of 1,3-divinyl-tetramethyldisiloxane, hexavinyldisiloxane, 1,3-divinyltetraphenyldisiloxane, 1,1,3-trivinyltrimethyldisiloxane, 1,3-tetravinyldimethyldisiloxane, 1,3,5-trivinyl-1,3,5-trimethylcyclotrisiloxane, 1,3,5,7-tetravinyl-1,3,5,7-tetramethylcyclotetrasiloxane, 1,3-divinyloctaphenylcyclopentasiloxane, and mixtures thereof.

27. (Original) The process according to Claim 18, wherein the one or more silicone monomers and/or oligomers containing the hydride functional group is selected from the group consisting of poly(methylhydrogen)siloxane, poly[(methylhydrogen)-co-(dimethyl)]siloxane; 1,3,5,7-tetramethylcyclotetrasiloxane, 1,3,5,7,9-decamethylcyclopentasiloxane, cyclic methylhydrogen siloxanes; tetrakis(dimethylsiloxy)silane, hydridodimethylsiloxy silicate $[\text{HSi}(\text{CH}_3)_2\text{O}_{1/2}]_2(\text{SiO}_2)$, and mixtures thereof.

28. (Amended) A process for forming a ceramic core, comprising:

mixing a ceramic powder with silicone monomers and/or oligomers to form a ceramic slurry, wherein the silicone monomers and/or oligomers comprise a volume of about 50% to about 75%, based on the total volume of green product, and contain

containing an alkenyl functionality of formula:
$$\begin{array}{c} \text{R}^1 \\ | \\ -\text{Si}-\text{X}_a-\text{C}=\text{C}- \\ | \quad \quad | \\ \text{R}^2 \quad \text{R}^3 \end{array}$$
 wherein R¹, R², and R³ each independently comprise hydrogen or a monovalent hydrocarbon radical, X is a divalent hydrocarbon radical, and a is 0 or 1 ~~a whole number having a value between 0 and 8, inclusive,~~ and a hydride functionality consisting of silicon-hydrogen bonds; wherein the silicone monomers and/or oligomers contain at least three alkenyl reactive functional groups or at least three hydride reactive functional groups per mole of monomer or oligomer; and have a viscosity of about 1 to about 1,000 centistokes;

Application No. 10/675,374
Amendment Dated August 6, 2006
Reply to Office Action Dated: June 7, 2006

125640-1

adding a metallic catalyst to the ceramic slurry;

transferring the ceramic slurry into a mold;

cross linking and/or polymerizing the silicone monomers and/or oligomers to form a green product; and

heating the green product to a temperature effective to decompose the crosslinked and/or polymerized silicone monomers and/or oligomers and form a silica char in the ceramic core.

29. (Original) The process according to Claim 28, further comprising sintering the green product.

30. (Original) The process according to Claim 28, wherein the ceramic slurry further comprises a solvent and the process further comprises drying the green product to remove the solvent and form a plurality of pores within the green product.

31. (Original) The process according to Claim 28, wherein the hydride reactive functional group and the alkenyl reactive functional groups are present at a molar ratio of 0.5 to 3.

32. (Original) The process according to Claim 28, wherein the ceramic slurry is free of a solvent.

33. (Canceled)